

SUN OMNIPROP™

ULTRA-LIGHTWEIGHT PROPPANT



EXCEPTIONAL PROPPANT PLACEMENT THROUGHOUT THE FRACTURE MATRIX FOR ENHANCED WELL PERFORMANCE

SUN OMNIPROP™ Ultra-Lightweight Proppant (ULWP) is designed for stimulation of unconventional wells to provide significantly greater fracture conductivity via unparalleled proppant placement in the far field fracture area and improved reservoir contact. SUN OMNIPROP™ is SUN's fourth generation advanced thermoset nanocomposite bead, featuring near-neutral buoyancy, high strength and thermal stability for application in most reservoirs with or without conventional proppants. This breakthrough ULWP provides technical resolution to the primary limitations which impair conventional proppant placement and performance. The high strength and near-neutral specific gravity of SUN OMNIPROP™ ULWP are designed to optimize proppant transport, placement, and conductivity longevity allowing you to **"Prop What You Frac!"**

Utilization: SUN OMNIPROP™ ULWP is used to provide effective propped fracture conductivity throughout the fracture network due to the material's low specific gravity and near-neutral buoyancy in water-based fluids. The addition of 3%-5% by weight to the overall proppant volume delivers significant production increases over conventional sand proppants alone.

Advantages of SUN OMNIPROP™ ULWP Over Conventional Proppants:

- ◆ Near-neutral buoyancy facilitates placement in far-field fractures.
- ◆ Perfect for slickwater or low-viscosity fluids; fewer fluid additives needed, minimizing damage risk.
- ◆ Chemically inert, physically smooth and spherical.
- ◆ Deformable - does not crush, chip, break, or generate migrating fines like sand proppants. Resists embedment preserving propped fracture width and residual conductivity
- ◆ No dust during handling for improved HSE compliance.
- ◆ Non-abrasive - will not damage tubing, pumps or surface equipment during application or production.
- ◆ Manifests excellent dissipation of static electricity, facilitating ease in handling.
- ◆ No sticky resin coatings to impact fluid performance, pumping, or production equipment.

Technical Data

API RP 19C/ISO 13503-2:

◆ Specific Gravity	1.066 g/cm ³
◆ Bulk Density	41.8 lbs/ft ³
◆ Absolute Density	66.8 lbs/ft ³
◆ Sphericity & Roundness	Both > 0.9
◆ Acid Solubility	< 1%
◆ Turbidity	26
◆ U.S. Mesh Sizes	14/40, 30/80, others
◆ Size Distribution	Meets/Exceeds Standards
◆ Median Diameter	(mm/in)
14/40	0.762 / 0.030
30/80	0.313 / 0.012
◆ Crush Resistance	> 15 Kpsi
◆ Fines Generation	< 0.5% at 8,000 psi


API RP 19D/ISO-13503

◆ Reference Conductivity	0.02 lbs/ft ² , 250°F, 6,000 psi, 50 hrs
14/40	– 121 mD-ft
30/80	– 482 mD-ft

Application Recommendations

◆ BHST Maximum*	350°F
◆ Closure Stress Maximum*	14,000 psi
◆ Application Rate	0.02 lbs/ft ²

*Well conditions exceeding recommendations should be considered case-by-case.



SUN...The HOLE Solution Company!
USA Toll Free 1.800.962.6490
Canada 403.319.0677
www.SolutionsBySun.com
Solutions@SunDrilling.com